

Amendments to the Abstract:

Please rewrite the Abstract as shown below:

Abstract

A joined body and method of producing the joined body are provided. A first member 10 containing at least eeramies-a ceramic and a second member 12 containing at least one of a metal or-and a metal composite was-are joined with each other. An via a metal adhesive, 2 composed of a The metal containing adhesive contains at least indium and materials 1A, 1B at least one material containing at least a component capable of reducing the melting point of indium and is provided between the first and second members to provide a laminate 13. The laminate 13 is heated at a temperature in a solid-liquid coexisting range of an alloy comprising indium and said-the indium melting point reducing component to join the first member 10 and second member 12 and second members.